


IN THE CLAIMS:


1. (Original) A hyperbranched polymer comprising at least one anhydrosugar-related compound selected from a dianhydrosugar alcohol represented by the following general formula [1]:



(wherein R is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms, provided that nR's are equal to or different from one another and at least one R of nR's is hydrogen atom, and

symbol n is an integer from 1 to 10)


and an anhydrosugar alcohol represented by the following general formula [2]:



(wherein R₁ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; R₂ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; R₃ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; and R₄ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; provided that R₁, mR₂'s, pR₃'s and R₄ are equal to or different from one another and at least one R₂ or R₃ of said mR₂'s and pR₃'s is hydrogen atom, respectively; and

symbol m is zero (0) or an integer from 1 to 20 and symbol p is an integer from 1 to 20, provided that symbol m+p is an integer from 1 to 20).


2. (Original) A hyperbranched polymer comprising at least one anhydrosugar-related compound selected from a dianhydrosugar alcohol represented by the following general formula [1]:



(wherein R is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms, provided that nR's are equal to or different from one another and at least one R of nR's is hydrogen atom, and

symbol n is an integer from 1 to 10)

and, an anhydrosugar alcohol represented by the following general formula [2]:




(wherein R₁ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; R₂ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; R₃ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; and R₄ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; provided that R₁, mR₂'s, pR₃'s and R₄ are equal to or different from one another and at least one R₂ or R₃ of said mR₂'s and pR₃'s is

hydrogen atom, respectively; and


symbol m is zero (0) or an integer from 1 to 20 and symbol p is an integer from integer from 1 to 20, provided that m+p is an integer from 1 to 20)

with at least one sugar compound selected from an anhydrosugar as represented by the following general formula [3]:




(3)

by the following general formula [4]:



(4)

by the following general formula [5]:




(5)

by the following general formula [6]:



and by the following general formula [7]:



(wherein R⁵ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; R⁶ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; and R⁷ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; provided that R⁵, R⁶ and R⁷ are equal to or different from one another).

3. (Currently Amended) The hyperbranched polymer as claimed in claim 1 or 2, wherein said hydrocarbon group is an alkyl group having from 1 to 30 carbon atoms, an aryl group having from 6 to 30 carbon atoms or an arylalkyl group having from 7 to 30 carbon atoms.
4. (Currently Amended) The hyperbranched polymer as claimed in claim 1 or 2, wherein said hydrocarbon group is an alkyl group having from 1 to 4 carbon atoms, an aryl group having from 6 to 12 carbon atoms or an arylalkyl group having from 7 to 10 carbon atoms.


5. (Currently Amended) The hyperbranched polymer as claimed in claim 1 ~~or~~ 2, wherein said dianhydrosugar alcohol [1] is a 1,2:5,6-dianhydro-D-mannitol-type compound, a 1,2:5,6-dianhydro-L-iditol-type compound, a 1,2:5,6-dianhydro-annitol-type compound, a 1,2:5,6-dianhydro-galactitol-type compound, a 1,2:5,6-dianhydro-glucitol-type compound or a 1,2:5,6-dianhydro-xylitol-type compound.

6. (Currently Amended) The hyperbranched polymer as claimed in claim 1 ~~or~~ 2, wherein said anhydrosugar alcohol [2] is a 1,2-anhydro-D-mannitol-type compound, a 1,2-anhydro-L-iditol-type compound, a 1,2-anhydro-annitol-type compound, a 1,2-anhydro-galactitol-type compound, a 1,2-anhydro-glucitol-type compound, a 1,2-anhydro-xylitol-type compound or a 1,2-anhydro-threitol-type compound.

7. (Currently Amended) The hyperbranched polymer as claimed in claim 1 ~~or~~ 2, wherein a degree of branching is from 0.05 to 1.00.

8. (Currently Amended) The hyperbranched polymer as claimed in claim 1 ~~or~~ 2, wherein a degree of branching is from 0.45 to 1.00.


9. (Original) A process for the preparation of a hyperbranched polymer comprising polymerizing at least one anhydrosugar-related compound selected from a dianhydrosugar alcohol represented by the following general formula [1]:



(wherein R is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms, provided that nR's are equal to or different from one another and at least one R of nR's is hydrogen atom, and

symbol n is an integer from 1 to 10)

and an anhydrosugar alcohol represented by the following general formula [2]:



wherein R₁ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; R₂ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; R₃ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; and R₄ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; provided that R₁, mR₂'s, pR₃'s and R₄ are equal to or different from one another and at least one R₂ or R₃ of said mR₂'s and pR₃'s is hydrogen atom, respectively; and

symbol m is zero (0) or an integer from 1 to 20 and symbol P is an integer from 1 to 20, provided that symbol m+p is an integer from 1 to 20)

in the presence of a cationic initiator or an anionic initiator.


10. (Original) A process for the preparation of a hyperbranched polymer, comprising polymerizing at least one anhydrosugar-related compound selected from a dianhydrosugar alcohol represented by the following general formula [1]:



(wherein R is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms, provided that nR's are equal to or different from one another and at least one R of nR's is hydrogen atom, and

symbol n is an integer from 1 to 10)

and an anhydrosugar alcohol represented by the following general formula [2]:




(wherein R₁ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; R₂ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; R₃ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; and R₄ is hydrogen atom or a


hydrocarbon group having from 1 to 30 carbon atoms; provided that R_1 , mR_2 's, pR_3 's and R_4 are equal to or different from one another and at least one R_2 or R_3 of said mR_2 's and pR_3 's is hydrogen atom, respectively; and

symbol m is zero (0) or an integer from 1 to 20 and symbol p is an integer from 1 to 20, provided that symbol $m+p$ is an integer from 1 to 20)

with at least one sugar compound selected from an anhydrosugars as represented by the following general formula [3]:



by the following general formula [4]:



by the following general formula [5]:



by the following general formula [6]:



by the following general formula [7]:



(wherein R⁵ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms;

R⁶ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms; and

R⁷ is hydrogen atom or a hydrocarbon group having from 1 to 30 carbon atoms;

however, provided that R⁵, R⁶ and R⁷ are equal to or different from one another)

in the presence of a cationic initiator or an anionic initiator.

11. (Currently Amended) The method for the preparation of the hyperbranched polymer as claimed in claim 9 or 10, wherein said hydrocarbon group is an alkyl group having from 1 to 4 carbon atoms, an aryl group having from 6 to 12 carbon atoms or an arylalkyl group having from 7 to 10 carbon atoms.

12. (Currently Amended) The method for the preparation of the hyperbranched polymer as claimed in claim 9 or 10, wherein said dianhydrosugar alcohol [1] is a 1,2:5,6-dianhydro-D-

mannitol-type compound, a 1,2:5,6-dianhydro-L-identol-type compound, a 1,2:5,6-dianhydro-alitol-type compound, a 1,2:5,6- ~~lc~~,c dianhydro-galactitol-type compound, a 1,2:5,6-dianhydro-glucitol-type compound or a 1,2:5,6- dianhydro-xylitol-type compound.

13. (Currently Amended) The method for the preparation of the hyperbranched polymer as claimed in claim 9 ~~or 10~~, wherein said anhydrosugar alcohol [2] is a 1,2-anhydro-D-mannitol-type compound, a 1,2- anhydro-L-identol-type compound, a 1,2-anhydro-annitol-type compound, a 1,2-anhydro-galactitol-type compound, a 1,2-anhydro-glucitol-type compound, a 1,2-anhydro-xylitol-type compound or a 1,2-anhydro-threitol-type compound.

14. (Currently Amended) The method for the preparation of the hyperbranched polymer as claimed in claim 9 ~~or 10~~, wherein said cationic initiator is a thermal cationic initiator, a photo cationic initiator, a Lewis acid or a Brenstead's acid.

15. (Currently Amended) The method for the preparation of the hyperbranched polymer as claimed in claim 9 ~~or 10~~, wherein said cationic initiator is sulphonium antimonate, boron trifluoride diethyl etherate, tin tetrachloride, antimony pentachloride, phosphorus pentachloride or trifluoromethane sulfonic acid.

16. (Currently Amended) The method for the preparation of the hyperbranched polymer as claimed in claim 9 ~~or 10~~, wherein said anionic initiator is a hydroxide or a metal alcolate.


17. (Currently Amended) The method for the preparation of the hyperbranched polymer as claimed in claim 9 ~~or 10~~, wherein said anionic initiator is KOH, tert-BuOK or $\text{Zn}(\text{OCH}_3)_2$.

18. (Currently Amended) The method for the preparation of the hyperbranched polymer as claimed in claim 9 ~~or 10~~, wherein said cationic initiator or said anionic initiator is used at the rate of 1 to 10% by weight of starting anhydrosugar-related compound.

19. (Currently Amended) The method for the preparation of the hyperbranched polymer as claimed in claim 9 ~~or 10~~, wherein a degree of branching is from 0.05 to 1.00.

20. (Currently Amended) The method for preparation of the hyperbranched polymer as claimed in claim 9 ~~or 10~~, wherein a degree of branching is from 0.45 to 1.00.

Respectfully submitted,


George A. Loud
Reg. No. 25,814

Dated: February 2, 2004

LORUSSO, LOUD & KELLY
3137 Mount Vernon Avenue
Alexandria, VA 22305
(703) 739-9393